

# FRIT ANALYSIS & OXIDE EFFECTS

## REFERENCE CHARTS

### Lead-Free Ferro Frits: Analysis

Frit	Cone	$K_2O$	$Na_2O$	$CaO$	$MgO$	$BaO$	$ZnO$	$B_2O_3$	$Al_2O_3$	$SiO_2$	$ZrO_2$	$F$
3110	07	2.5	15.4	5.2	0.8	--	--	2.8	3.7	69.60	--	--
3124	05	0.6	5.6	14.5	--	--	--	12.5	10.0	56.80	--	--
3134	07	--	10.2	20.1	--	--	--	23.2	--	46.50	--	--
3185	??	--	1.0	--	--	--	--	4.43	--	7.27	--	--
3195	05	--	12.7	11.3	--	--	--	15.8	12.5	47.60	--	--
3240	05	0.6	4.5	8.8	--	7.9	15.8	10.0	0.9	39.50	10.2	--
3269	07	10.0	11.2	--	--	--	--	17.1	12.8	48.90	--	--
3270	??	.159	.380	.461	--	--	--	.648	.232	2.34	--	--
3278	03	--	15.5	6.8	--	--	--	21.8	--	56.20	--	--
3289	07	--	5.5	--	--	27.4	--	12.4	5.4	49.30	--	--
3293	05	--	16.7	0.2	0.8	--	--	--	5.9	76.40	--	--
5301	05	5.1	19.2	2.3	--	--	--	11.7	11.3	41.80	--	8.6

### Lead-Bearing Ferro Frits: Analysis

Frit	Cone	$K_2O$	$Na_2O$	$CaO$	$MgO$	$BaO$	$ZnO$	$PbO$	$B_2O_3$	$Al_2O_3$	$SiO_2$	$ZrO_2$
3300	03	3.2	0.7	8.8	6.2	6.2	10.5	22.2	--	9.2	38.8	--
3304	07	--	2.1	--	--	--	--	52.6	--	4.8	40.5	--
3403	07	1.4	0.3	0.1	--	--	--	67.8	--	2.4	28.1	--
3417	07	1.8	1.6	4.4	--	--	--	30.4	12.6	3.1	43.1	2.4
3419	09	--	6.5	--	--	--	--	59.2	14.5	--	19.8	--
3465	03	--	14.7	6.6	--	--	--	6.60	19.3	--	52.8	--
3467	03	1.8	2.4	8.5	0.7	--	--	17.4	4.5	9.2	55.7	--
3481	03	1.4	3.1	9.9	--	--	--	23.1	6.0	7.1	49.4	--
3489	09	--	--	5.6	--	--	--	67.6	--	--	26.8	--
3493	07	1.9	1.5	4.6	--	--	--	31.3	12.9	3.1	44.7	--

### Fusion Frits: Analysis

Frit	Cone	$K_2O$	$Na_2O$	$CaO$	$MgO$	$BaO$	$ZnO$	$B_2O_3$	$Al_2O_3$	$SiO_2$	$ZrO_2$	$Li_2O$	Expansion
F2	1600° F	3.7	03.0	10.5	--	--	--	20.3	13.5	49.0	--	--	7.19
F12	1450° F	--	10.4	20.0	--	--	--	23.8	0.8	45.0	--	--	8.18
F280	1550° F	0.6	7.0	14.2	--	--	--	15.0	8.5	54.8	--	--	7.90
F403	1825° F	--	0.5	4.8	--	35.0	--	1.5	6.2	49.0	3.0	--	6.92
F493	1300° F	6.0	11.7	--	--	--	--	13.2	6.3	51.8	--	11.0	14.13
F537	>1850° F	--	2.0	28.0	--	--	--	10.0	3.0	57.0	--	--	7.70

### Equivalent Frit Compositions

#### Lead-Free Frits

Ferro	Pemco	O-Homel
3110	P1505	--
3124	P311	90
3134	P54	14 (242)
3240	P64	26 (69)
3269	P25	25 (259)
3278	P830	K3
3289	P626	400
3293	P283	--
3270	P802	378
CC270	--	642

#### Oxide Effects on Surface Tension

##### HIGH SURFACE TENSION

- ... Alumina
- ... Magnesia
- ... Zirconia
- ... Calicia
- ... Tin Oxide
- ... Stontia
- ... Baria
- ... Silica
- ... Titania
- ... Boric Oxide
- ... Lithia
- ... Lead Oxide
- ... Soda
- ... Potash

##### LOW SURFACE TENSION

#### Lead-Bearing Frits

Ferro	Pemco	O-Homel
3300	--	316
3304	--	61
3403	Pb723	71 (243)
3417	Pb63	24 (235)
3419	Pb83	33 (240)
3465	Pb943	18
3467	--	365
3481	--	403
3489	Pb716	--
3493	Pb742	373

#### Gerstley Borate Substitutes

Oxide	Gerstley	Laguna	Ferro	Boraq	Cady Cal	
	Borate	CC298	#2	100	Ulexite	Frit 439
$B_2O_3$	29.00	27.5	28.0	30.9	48.6	41.4
$Na_2O$	4.50	4.0	6.0	3.1	--	0.1
$CaO$	22.00	18.9	21.0	22.1	25.3	26.5
$MgO$	3.50	2.3	3.5	3.5	0.3	1.8
$K_2O$	0.25	1.4	3.5	0.5	--	--
$Fe_2O_3$	0.20	0.1	--	0.2	--	1.7
$SrO$	--	--	--	0.2	--	0.7
$TiO_2$	--	0.1	--	--	--	--
$Al_2O_3$	1.80	8.1	--	2.5	2.3	0.1
$SiO_2$	10.00	18.7	31.0	11.2	0.7	5.0

# GROG & RAW CLAY ANALYSIS

## GROG ANALYSES

### Chemical Analysis

Al <sub>2</sub> O <sub>3</sub> .....	46.80%
SiO <sub>2</sub> .....	50.00%
TiO <sub>2</sub> .....	1.89%
Fe <sub>2</sub> O <sub>3</sub> .....	0.95%
CaO.....	0.04%
MgO.....	0.08%
Na <sub>2</sub> O .....	0.09%
K <sub>2</sub> O.....	0.09%
P <sub>2</sub> O <sub>5</sub> .....	0.09%

### Physical Properties

Bulk Density ((ASTM C-357, gm/cc).....	2.62
Apparent Porosity Percentage.....	3.60
PCE .....	35 (3245°F)
2800°F Reheat Change:	
B.D. gm/cc .....	2.60
Volume Percentage .....	+0.80
2910°F Reheat Change:	
B.D. gm/cc .....	2.54
Volume Percentage .....	+3.10
Mineralogy:	
Mullite Percentage .....	65.00
Glass Percentage .....	20.00
Cristobalite Percentage .....	15.00

### Grain Size Specifications (Percentage Retained)

	20	28	35	48	60	100	200	PAN
CH551	Tr-5	5-20	10-30	-	20-40	10-30	-	5-25
CH527	Tr-5	-	Tr-10	10-20	-	40-60	10-30	5-15
CH533	-	-	Trace	-	-	-	35-45	55-65
	20	30	40	50	70	100	200	PAN
CH563	0-5	(Even Dist.)	80-93	7-12	-	-	2 max	low

\* Grain size is measured by the percentage of particles retained by screens of various mesh sizes. PAN designates the percentage passing the last reported screen for each size.

### RAW CLAY ANALYSIS

Percentages given are close estimates and should be regarded as approximate.

Name	SO <sub>4</sub>	SiO <sub>2</sub>	Al <sub>2</sub> O <sub>3</sub>	FeO <sub>3</sub>	Fe <sub>2</sub> O <sub>3</sub>	Fe <sub>3</sub> O <sub>4</sub>	CaO	TiO <sub>2</sub>	MgO	Loss on Ignition	Impurities	Alkaline	Moisture	Cone Equiv.
Albany Slip (True)	--	57.64	14.66	--	5.20	--	--	0.40	2.68	9.46	3.25◆	0.80✚	Trace	13
Alberta Slip	--	57-58	15-17	--	4.5-5.0	--	6.0-7.0	Trace	3.0-4.0	7.30	1.00	3.0-4.0	--	--
AP Green Fireclay	--	50-54	19-23	--	1.5-2.5	--	0.1-0.6	1.5-2.5	0.1-0.6	10-12	0.5-1.5	0.5-1.5	--	--
Barnard Clay	--	59.80	11.54	--	4.13	--	6.20	--	--	10.40	--	--	--	3-4
C-1 Clay	--	73.00	14.80	--	0.40	--	1.30	--	0.50	6.30	1.70◆	0.20✚	--	--
Dover Fireclay	--	41.43	6.77	--	29.94	--	--	--	--	8.41	--	--	--	29
Greenstripe Fireclay	--	57.20	27.70	--	2.00	--	--	--	--	10.30	--	1.30	--	28-30
Hawthorne Bond Clay	--	55.10	39.11	--	1.02	--	0.15	2.08	0.85	--	0.10✚	0.12●	0.07✖	--
J-2	--	56.70	28.40	--	1.10	--	0.40	1.70	0.30	10.80	0.50	0.10	--	--
Jordan Ball Clay	--	54.10	27.98	3.58	--	--	--	1.50	--	11.12	3.80	--	--	31-32
Kaolin, Calcined	--	67.19	20.23	1.73	--	--	--	--	--	6.89	--	2.23	--	26-27
Kaolin, EPK	--	53.80	44.40	0.44	--	--	0.24	1.55	--	--	0.50	--	--	--
Kaolin, English Grolleg	--	46.00	37.00	--	--	--	--	--	--	14.00	--	--	--	35
Kaolin, Hemer	--	41.00	36.00	--	1.30	--	0.48	1.13	0.26	13.22	0.53◆	0.08✚	--	--
Kaolin, McNamee	--	44.46	39.34	--	0.33	--	0.06	1.20	0.05	13.99	0.31	0.04	--	--
Kaolin, Pioneer	--	47.70	37.20	--	--	--	--	--	--	--	--	--	-2.00	87
Kaolin, Sapphire	--	46.30	38.20	0.70	--	--	0.20	1.40	0.20	13.40	--	0.01	--	33-34
Kaopaque 20	--	45.20	39.20	--	0.32	--	0.21	0.66	0.03	13.92	0.03◆	0.03✚	--	--
Kentucky OM4 Ball Clay	--	55.90	27.20	--	1.10	--	0.40	1.20	0.40	13.51	--	0.18	--	34
Kentucky Special	--	54.50	27.50	--	1.20	--	0.50	1.30	0.50	13.30	1.10	0.10	--	--
Kentucky Stone	--	67.20	20.80	--	1.30	--	0.30	1.40	0.50	7.10	1.30	0.10	--	--
Lincoln 60 Fireclay	--	52.10	31.15	--	--	--	--	--	--	12.04	--	--	--	32
Masons Blend Fireclay	--	52.00	29.00	2.00	--	--	--	--	--	12.40	--	19□	--	31
Mexico Fireclay	--	51.30	31.70	--	2.20	--	0.50	1.40	0.86	--	--	0.45	--	--
MT Light	--	60.30	26.30	--	1.30	--	0.40	1.30	0.40	9.20	0.60	0.20	--	--
Newman Red Clay	--	53.41	30.41	1.61	--	--	0.28	1.35	0.22	11.22	--	1.41	--	31
Old Hickory #5 Ball Clay	--	58.56	26.17	--	1.04	--	0.08	1.50	0.22	10.65	0.89	0.12	--	--
Pine Lake Fireclay	--	59.20	21.49	--	7.71	0.05	0.98	0.22	7.30	--	1.09	2.39	--	--
PV Clay 200m	--	58.60	27.30	--	1.50	--	0.30	1.90	0.10	9.50	--	0.80	--	29-30
Red Mesa Fireclay	--	75.93	14.82	--	--	--	--	--	--	1.92	--	6.10	--	17
Tennessee SGP1 Ball Clay	0.01	54.50	17.70	--	8.04	--	0.10	--	0.86	9.04	--	3.43	1.60	low
United Yellowbanks 401	--	57.00	27.60	--	1.50	--	0.30	1.30	0.70	8.50	2.60◆	0.50	2.50	31
XX Saggars	--	56.70	29.20	--	0.70	--	0.50	1.70	0.30	9.80	0.90	0.30	--	--

**BULLET CODES** for Impurities & Alkaline Components: ◆ = K<sub>2</sub>O    ✚ = Na<sub>2</sub>O    ● = P<sub>2</sub>O<sub>5</sub>    ✷ = SO<sub>4</sub>    □ = K<sub>2</sub>O